

ADDENDUM #1
Clinton Park Tennis and Basketball Court Renovations
ITB 4295
Due: Thursday, June 20, 2013 by 10:30 a.m.

The following changes, additions, and/or deletions shall be made to the Invitation to Bid for Clinton Park Tennis and Basketball Court Renovations, ITB No. 4295, on which bids will be received on or before 10:30 A.M. Thursday, June 20, 2013.

The information contained herein shall take precedence over the original document and is appended thereto. This Addendum includes 2 pages and no drawing(s).

Bidders are to acknowledge receipt of this Addendum No. 1 on page ITB-1 of the Bid Documents prior to submitting a Bid.

Changes in the Bid Documents which are outlined below are referenced to a page or drawing in which they appear conspicuously. The Bidder is to take note in its review of the documents and include these changes as they affect work or details in other areas not specifically referenced her.

Item #1 ***NEW BID REQUIREMENT***
DETAILED SPECIFICATION FOR TENNIS COURT COLOR COATING

DESCRIPTION

The work covered by these specifications consists of furnishing all labor, equipment and materials, and performing all operations in connection with color coating and striping. Prior to applying color coat system, the net sleeves, center strap anchor and fencing shall be installed by contractor. New asphalt shall be allowed to cure for 30 days prior to application of color coat.

SURFACE PREPARATION

Allow asphalt to cure for 14 days. Any depressions or 'bird baths' that cover a nickel shall be marked and repaired with acrylic patch mix. Surfaces shall be broom cleaned, power washed or prepared sufficiently to receive color coating materials as per manufacturer's requirements.

SURFACING MATERIAL

1. Acrylic Resurfacer - 1 coat. Surface shall be uniform texture, clean and free of grease, oils and other foreign materials. Mix shall be the following: 55 gallons acrylic resurfacer, 20-40 gallons water, 600-900 lbs sand. The application rate shall be .05-.07 gallons per square yard.
2. Fortified Plexi-pave - 2 coats - 1st coat shall be applied at a rate of .1-.07 gallons per square yard. Second coat shall be applied at a rate of .07-.05 gallons per square yard.
3. Line Paint - all 2" lines are to be taped on each side of line and laid out as per attached plan sheets. Paint is to be acrylic latex striping.

4. Color shall be blue inside the lined section of the separate courts, and green between the courts and to the edge of asphalt. Colors shall be approved by City prior to application.